



**Resene ArmourX Cold Galv  
RA23**

**Technical Product Data Sheet  
coming soon**

**New Zealand:**

PO Box 38242, Wellington Mail Centre, Lower Hutt 5045

Phone: +64 (4) 577 0500, 0800 RESENE (737 363)

Email: [advice@resene.co.nz](mailto:advice@resene.co.nz)

Website: [www.resene.co.nz](http://www.resene.co.nz)

**Australia:**

PO Box 924, Beenleigh, Queensland 4207

Phone: 1800 738 383

Email: [advice@resene.com.au](mailto:advice@resene.com.au)

Website: [www.resene.com.au](http://www.resene.com.au)